



	GENESI ALLUMINIO / GENESI CARBONIO 360 EVO											EGO CARBONIO						
	HALO BASE			HALO CLEAR			HVLP			GEO			HALO			HVLP		
	nozzle diameter	pressure to calcium psi	calcium bar	nozzle diameter	pressure to calcium psi	calcium bar	nozzle diameter	pressure to calcium psi	calcium bar	nozzle diameter	pressure to calcium psi	calcium bar	nozzle diameter	pressure to calcium psi	calcium bar	nozzle diameter	pressure to calcium psi	calcium bar
PERMACRON MIXING 293	1.2 B	24.5	1.7				1.2	26	1.8	1.2	26	1.8	1.2	21.5	1.5	1.2	21.5	1.5
BASISLACK 280	1.2 B	24.5	1.7				1.2	26	1.8	1.2	26	1.8	1.2	21.5	1.5	1.2	21.5	1.5
MISCELACK 480	1.1 B	24.5	1.7				1.1	26	1.8	1.1	26	1.8	1.2	21.5	1.5	1.2	21.5	1.5
WET BED (BLENDER WATER BASE)	1.1 B	24.5	1.7				1.1	26	1.8	1.1	26	1.8	1.2	24.5	1.7	1.2	24.5	1.7
MS - HS CLEARCOAT				1.2-1.3 C	29	2	1.3	29	2	1.3	29	2	1.2	21.5	1.5	1.2	21.5	1.5
UHS CLEARCOAT				1.2-1.3 C	29	2	1.2	29	2	1.2	29	2	1.2	21.5	1.5	1.2	21.5	1.5
1 K CLEARCOAT				1.3 C	29	2	1.3	29	2	1.3	29	2	1.2	21.5	1.5	1.2	21.5	1.5
AIR TECH CLEARCOAT				1.2 C	29	2	1.2	29	2	1.2	29	2	1.2	21.5	1.5	1.2	21.5	1.5
MATT CLEARCOAT				1.3 C	29	2	1.3	29	2	1.3	29	2						
WATER CLEARCOAT																		
BLENDER CLEAR (SPOT BLENDER)													1	21.5	1.5	1	21.5	1.5
2 K TOPCOAT				1.3 C	29	2	1.3	29	2	1.3	29	2	1.2	21.5	1.5	1.2	21.5	1.5
SEALER TRASPARENT				1.4 C	29	2	1.4	29	2	1.4	29	2						
WATER SEALER																		
NON SANDIG SURFACER - wet on wet				1.4 C	29	2	1.4	29	2	1.4	29	2						
UV PRIMER FILLER													1.2	21.5	1.5	1.2	21.5	1.5

	SLIM KOMBAT						SLIM XLIGHT						SLIM					
	HALO			HVLP			HALO			HVLP			HALO			HVLP		
	nozzle diameter	pressure to calcium psi	calcium bar	nozzle diameter	pressure to calcium psi	calcium bar	nozzle diameter	pressure to calcium psi	calcium bar	nozzle diameter	pressure to calcium psi	calcium bar	nozzle diameter	pressure to calcium psi	calcium bar	nozzle diameter	pressure to calcium psi	calcium bar
PERMACRON MIXING 293	1.3	26	1.8	1.3	29	2	1.3	26	1.8	1.3	29	2	1.3	26	1.8	1.3	29	2
BASISLACK 280	1.3	26	1.8	1.3	29	2	1.3	26	1.8	1.3	29	2	1.3	26	1.8	1.3	29	2
MISCELACK 480	1.2	26	1.8	1.2	29	2	1.2	26	1.8	1.2	29	2	1.2	26	1.8	1.2	29	2
WET BED (BLENDER WATER BASE)	1.2	26	1.8	1.2	29	2	1.2	26	1.8	1.2	29	2	1.2	26	1.8	1.2	29	2
MS - HS CLEARCOAT	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2
UHS CLEARCOAT	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2
1 K CLEARCOAT	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2
AIR TECH CLEARCOAT	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2
MATT CLEARCOAT	1.4	29	2	1.4	29	2	1.4	29	2	1.4	29	2	1.4	29	2	1.4	29	2
WATER CLEARCOAT																		
BLENDER CLEAR (SPOT BLENDER)	1.2	29	2	1.2	29	2	1.2	29	2	1.2	29	2	1.2	29	2	1.2	29	2
2 K TOPCOAT	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2
SEALER TRASPARENT	1.5	29	2	1.5	29	2	1.5	29	2	1.5	29	2	1.5	29	2	1.5	29	2
WATER SEALER																		
NON SANDIG SURFACER - wet on wet	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2
UV PRIMER FILLER	1.2	29	2	1.2	29	2	1.2	29	2	1.2	29	2	1.2	29	2	1.2	29	2
PRIMER	1.5	29	2	1.5	29	2	1.5	29	2	1.5	29	2	1.5	29	2	1.5	29	2
WATER PRIMER																		
HI - BUILD SANDING	1.7	29	2	1.7	29	2	1.8	29	2	1.8	29	2	1.8	29	2	1.8	29	2
SPRAY PUTTY	2.5	24.5	1.7				2.5	24.5	1.7				2.5	24.5	1.7			