



	GENESI ALLUMINIO / GENESI CARBONIO 360 EVO												EGO CARBONIO					
	HALO BASE			HALO CLEAR			HVLP			GEO			HALO			HVLP		
	nozzle diameter	pressure to psi	calcium bar	nozzle diameter	pressure to psi	calcium bar	nozzle diameter	pressure to psi	calcium bar	nozzle diameter	pressure to psi	calcium bar	nozzle diameter	pressure to psi	calcium bar	nozzle diameter	pressure to psi	calcium bar
DELTRON BC	1.3 B	24.5	1.7				1.3	29	2	1.3	29	2	1.2	21.5	1.5	1.2	21.5	1.5
ENVIROBASE	1.2 B	24.5	1.7				1.2	26	1.8	1.2	26	1.8	1.2	21.5	1.5	1.2	21.5	1.5
WATER BASE NEW																		
WET BED (BLENDER WATER BASE)	1.2 B	24.5	1.7				1.2	26	1.8	1.2	26	1.8	1.4	24.5	1.7	1.4	24.5	1.7
MS - HS CLEARCOAT				1.2-1.3 C	29	2	1.3	29	2	1.3	29	2	1.2	21.5	1.5	1.2	21.5	1.5
UHS CLEARCOAT				1.2-1.3 C	29	2	1.2	29	2	1.2	29	2	1.2	21.5	1.5	1.2	21.5	1.5
1 K CLEARCOAT				1.2 C	29	2	1.2	29	2	1.2	29	2	1.2	21.5	1.5	1.2	21.5	1.5
AIR TECH CLEARCOAT				1.2 C	29	2	1.2	29	2	1.2	29	2	1.2	21.5	1.5	1.2	21.5	1.5
MATT CLEARCOAT				1.3 C	29	2	1.3	29	2	1.3	29	2	1.2	21.5	1.5	1.2	21.5	1.5
WATER CLEARCOAT				1.3 C	29	2	1.3	29	2	1.3	29	2	1.2	21.5	1.5	1.2	21.5	1.5
BLENDER CLEAR (SPOT BLENDER)													1.0	21.5	1.5	1	21.5	1.5
2 K TOPCOAT				1.3 C	29	2	1.3	29	2	1.3	29	2	1.2	21.5	1.5	1.2	21.5	1.5
SEALER TRASPARENT				1.4 C	26	1.8	1.4	29	2	1.4	29	2						
WATER SEALER																		
NON SANDIG SURFACER - wet on wet				1.3 C	29	2	1.3	29	2	1.3	29	2						
UV PRIMER FILLER													1.2	21.5	1.5	1.2	21.5	1.5

	SLIM KOMBAT						SLIM XLIGHT						SLIM					
	HALO			HVLP			HALO			HVLP			HALO			HVLP		
	nozzle diameter	pressure to psi	calcium bar	nozzle diameter	pressure to psi	calcium bar	nozzle diameter	pressure to psi	calcium bar	nozzle diameter	pressure to psi	calcium bar	nozzle diameter	pressure to psi	calcium bar	nozzle diameter	pressure to psi	calcium bar
DELTRON BC	1.4	26	1.8	1.4	29	2	1.4	26	1.8	1.4	29	2	1.4	26	1.8	1.4	29	2
ENVIROBASE	1.3	26	1.8	1.3	29	2	1.3	26	1.8	1.3	29	2	1.3	26	1.8	1.3	29	2
WATER BASE NEW																		
WET BED (BLENDER WATER BASE)	1.3	26	1.8	1.3	29	2	1.3	26	1.8	1.3	29	2	1.3	26	1.8	1.3	29	2
MS - HS CLEARCOAT	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2
UHS CLEARCOAT	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2
1 K CLEARCOAT	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2
AIR TECH CLEARCOAT	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2
MATT CLEARCOAT	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2
WATER CLEARCOAT	1.4	29	2	1.4	29	2	1.4	29	2	1.4	29	2	1.4	29	2	1.4	29	2
BLENDER CLEAR (SPOT BLENDER)	1.2	29	2	1.2	29	2	1.2	29	2	1.2	29	2	1.2	29	2	1.2	29	2
2 K TOPCOAT	1.4	29	2	1.4	29	2	1.4	29	2	1.4	29	2	1.4	29	2	1.4	29	2
SEALER TRASPARENT	1.4	29	2	1.4	29	2	1.4	29	2	1.4	29	2	1.4	29	2	1.4	29	2
WATER SEALER																		
NON SANDIG SURFACER - wet on wet	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2	1.3	29	2
UV PRIMER FILLER	1.2	26	1.8	1.2	29	2	1.2	26	1.8	1.2	29	2	1.2	26	1.8	1.2	29	2
PRIMER	1.4	26	1.8	1.4	29	2	1.4	26	1.8	1.4	29	2	1.4	26	1.8	1.4	29	2
WATER PRIMER																		
HI - BUILD SANDING	1.7	29	2	1.7	29	2	1.8	29	2	1.8	29	2	1.8	29	2	1.8	29	2
SPRAY PUTTY	2.5	24.5	1.7				2.5	24.5	1.7				2.5	24.5	1.7			